



EPU 41

EPU 41 is a production-scale elastomeric material that is especially well-suited for elastomeric lattices where high resiliency is needed.



CarbonResin EPU 41

DOC #107171 REV A
TECHNICAL DATA SHEET, LAST UPDATED 05/02/18

Tensile Properties ASTM D412, Die-C Shape, 500 mm/min	Metric	U.S.
Ultimate Tensile Strength	6.2 MPa	900 psi
Elongation at Break	> 130 %	
Stress at 50 % Elongation	2.7 MPa	390 psi
Stress at 100 % Elongation	4.7 MPa	680 psi

Mechanical Properties	Metric	U.S.
Tear Strength, ASTM D624, Die-C (die cut)	20 kN/m	110 lb _f /in
Compression Set, 23 °C, 72 hrs, ASTM D395-B	22 %	
Bayshore Rebound Resilience, ASTM D2632	30 %	
Ross Flexing Fatigue, ASTM D1052 23 °C, 60 degree bending, 100 cycles/minute	> 50,000 cycles	
Ross Flexing Fatigue, ASTM D1052 -10 °C, 60 degree bending, 100 cycles/minute	> 40,000 cycles	

Thermal Properties	Metric	U.S.
T _g (DMA, tan(d)), ASTM D4065	-9 °C	16 °F

General Properties	Metric
Hardness, Shore A, ASTM D2240	73 (instant) 70 (5 sec)
Density, ASTM D792	1.027 g/cm ³
Relative Abrasion Volume Loss (ISO 4649 A)	66 mm ³



CarbonResin EPU 41

DOC #107171 REV A
TECHNICAL DATA SHEET, LAST UPDATED 05/02/18

The information in this document includes typical values from printing various parts and is intended for reference and comparison purposes only. This information should not be used for testing, design specification or quality control purposes. End-use material performance can be impacted by, but not limited to, design, processing, operating and end-use conditions, test conditions, color, etc. Actual values will vary with build conditions. In addition, product specifications are subject to change without notice.

This information and Carbon's technical advice are given to you in good faith but without warranty. The application, use and processing of these and other Carbon products by you are beyond Carbon's control and, therefore, entirely your own responsibility. Carbon products are only to be used by you subject to the terms of the written agreement by and between you and Carbon.

You are responsible for determining that the Carbon material is safe, lawful, and technically suitable for the intended application, as well as for identifying the proper disposal (or recycling) method consistent with applicable environmental laws and regulations. CARBON MAKES NO WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR USE, OR NON-INFRINGEMENT. Further, it is expressly understood and agreed that you assume and hereby expressly release Carbon from all liability, in tort, contract or otherwise, incurred in connection with the use of Carbon products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind Carbon. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.


EPU 41 Expanded TDS

EPU 41 Expanded TDS Table of Contents

- **Thermal properties**
 - DMA of EPU 40 vs. 41

EPU 41 vs. EPU 40 (DMA Dynamic Mechanical Analysis)

EPU 41 has improved cold temperature performance vs. EPU 40



EPU 41 has lower Tg (tanD peak), indicating retention of elastomeric properties down to colder temperatures

EPU 41 Tg(tanD) = -9°C
EPU 40 Tg(tanD) = 8°C